

# EMI Ferrite Bead



## BBGK Series



### Overview

EMI ferrite beads are made of ferrite material, which can block high-frequency noise while allowing required signals to pass through, providing high impedance and noise attenuation to improve signal integrity/efficiency and reduce power loss.

### Benefits

1. Compliance with EMI regulations.
2. Reduced power loss and improved system efficiency
3. Operating temperature range: -55 ~ +125°C
4. Improved signal integrity

### Applications

1. Wearable Devices
2. Industrial
3. Communications
4. Consumer Electronics

### Product Information


Series	Size Code (JIS/EIA)	Impedance ( $\Omega$ )
BBGK	1608/0603 2012/0805	10 ~ 2000



## BBGK00160808 Series Specification

**1** **Scope:** This specification applies to MULTILAYER FERRITE CHIP BEADS

**2** **Part Numbering:**



**3** **Rating:**

Operating Temperature: - 5 5 °C ~ 1 2 5 °C(Including self - temperature rise)

Storage Temperature: - 5 5 °C ~ 1 2 5 °C(after PCB)  
 - 5 °C~ 4 0 °C, Humidity 4 0 %~ 7 0 %(before PCB)

**4** **Marking:**


**No Marking**

**5** **Standard Testing Condition**

	Unless otherwise specified	In case of doubt
Temperature	Ordinary Temperature(15 to 35°C)	20 to 30°C
Humidity	Ordinary Humidity(25 to 85% RH)	50 to 80 %RH

## BBGK00160808 Series Specification

### 6 Configuration and Dimensions:



Dimensions in mm

TYPE	160808
A	1.6±0.15
B	0.8±0.15
C	0.8±0.15
D	0.3±0.20

Net Weight (grms)

Size Code	Net Weight (grms)
160808	0.00576

### 7 Electrical Characteristics:

Part No.	Impedance (Ω)	Test Freq.	RDC (Ω)Max.	Rated Current (mA)Max.
BBGK00160808100□00	10	100 MHz,200 mV	0.03	1000
BBGK00160808110□00	11	100 MHz,200 mV	0.03	1000
BBGK00160808300□00	30	100 MHz,200 mV	0.06	800
BBGK00160808400□00	40	100 MHz,200 mV	0.06	800
BBGK00160808500□00	50	100 MHz,200 mV	0.06	600
BBGK00160808600□00	60	100 MHz,200 mV	0.06	700
BBGK00160808700□00	70	100 MHz,200 mV	0.1	600
BBGK00160808800□00	80	100 MHz,200 mV	0.1	600
BBGK00160808101□00	100	100 MHz,200 mV	0.15	600
BBGK00160808121□00	120	100 MHz,200 mV	0.15	600
BBGK00160808151□00	150	100 MHz,200 mV	0.15	600
BBGK00160808181□00	180	100 MHz,200 mV	0.18	400
BBGK00160808201□00	200	100 MHz,200 mV	0.18	400
BBGK00160808221□00	220	100 MHz,200 mV	0.18	550
BBGK00160808301□00	300	100 MHz,200 mV	0.25	500
BBGK00160808331□00	330	100 MHz,200 mV	0.3	400
BBGK00160808471□00	470	100 MHz,200 mV	0.3	400
BBGK00160808601□00	600	100 MHz,200 mV	0.3	400
BBGK00160808102□00	1000	100 MHz,200 mV	0.45	300
BBGK00160808152□00	1500	100 MHz,200 mV	0.7	150

**NOTE:** □-tolerance Y=±25% / T=±30%


1. Operating temperature range - 5 5°C ~ 1 2 5°C(Including self - temperature rise)

2. Rate Current : Applied the current to coils, the temperature rise shall not be more than 30°C

## BBGK00160808 Series Specification

### 8 BBGK00160808 Series

#### 8.1 Construction:





#### 8.2 Material List:

No	Part	Material
1	Ferrite Substance	NiO-CuO-ZnO-Ferrite
2	Silver electrode	Ag
3	Silver electrode	Ag
4	Cu plating	Cu
5	Ni plating	Ni
6	Sn plating	Sn

## BBGK00160808 Series Specification

### 9 Reliability Of Ferrite Multilayer Chip Bead


#### 1-1.Mechanical Performance

No	Item	Specification	Test Method
1-1-1	Flexure Strength	The forces applied on the right conditions must not damage the terminal electrode and the ferrite	Test device shall be soldered on the substrate Substrate Dimension: 100x40x1.6mm Deflection: 2.0mm Keeping Time: 30sec  *For 100505, substrate dimension is 100x40x0.8mm
1-1-2	Vibration		Test device shall be soldered on the substrate Oscillation Frequency: 10 to 55 to 10Hz for 1min Amplitude: 1.5mm Time: 2hrs for each axis (X, Y & Z), total 6hrs
1-1-3	Resistance to Soldering Heat	Appearance: No damage More than 75% of the terminal electrode should be covered with solder. Impedance : within $\pm 30\%$ of initial value	Pre-heating: 150°C, 1min Solder Composition: Sn/Ag3.0/Cu0.5(Pb-Free) Solder Temperature: 260 $\pm$ 5°C Immersion Time: 10 $\pm$ 1sec
1-1-4	Solder ability	The electrodes shall be at least 95% covered with new solder coating	Pre-heating: 150°C, 1min Solder Composition: Sn/Ag3.0/Cu0.5(Pb-Free) Solder Temperature: 245 $\pm$ 5°C (Pb-Free) Immersion Time: 4 $\pm$ 1sec
1-1-5	Terminal Strength Test	No split termination  Chip Mounting Pad	Test device shall be soldered on the substrate, then apply a force in the direction of the arrow. Force : 5N Keeping Time: 10 $\pm$ 1sec

#### 1-2.Environmental Performance

No	Item	Specification	Test Method		
1-2-1	Temperature Cycle	Appearance: No damage Impedance: within $\pm 30\%$ of initial value	One cycle:		
			Step	Temperature (°C)	Time (min)
			1	-55 $\pm$ 3	30
			2	25 $\pm$ 2	3
			3	125 $\pm$ 3	30
4	25 $\pm$ 2	3			
			Total: 100cycles Measured after exposure in the room condition for 24hrs		
1-2-2	Humidity Resistance		Temperature: 40 $\pm$ 2°C Relative Humidity: 90 ~ 95% / Time: 1000hrs Measured after exposure in the room condition for 24hrs		
1-2-3	High Temperature Resistance		Temperature: 125 $\pm$ 3°C / Relative Humidity: 0% Applied Current: Rated Current /Time: 1000hrs Measured after exposure in the room condition for 24hrs		
1-2-4	Low Temperature Resistance		Temperature: -55 $\pm$ 3°C Relative Humidity: 0% / Time: 1000hrs Measured after exposure in the room condition for 24hrs		

## BBGK00160808 Series Specification



Lead-Free(LF)標準溫度分析範圍

Refer to J-STD-020C

管制項目 Item.	升溫區 Ramp-up	預熱區 Pre-heating	迴焊區 Reflow	Peak Temp	冷卻區 Cooling
溫度範圍 Temp.scope	R.T ~ 150°C	150°C ~ 200°C	Above 217°C	260±5°C	Peak Temp.~150°C
標準時間 Time spec.	-	60 ~ 180 sec	60 ~ 150 sec	20 ~ 40 sec	-
實際時間 Time result	-	75 ~ 100 sec	90 ~ 120 sec	20 ~ 35 sec	-

NOTE :


1. Re-flow possible times : within 2 times
2. Nitrogen adopted is recommended while in re-flow
3. Products can only be soldered with reflow

## BBGK00160808 Series Specification

### 11 Packaging:

#### 11.1 Packaging -Cover Tape


The force for tearing off cover tape is 10 to 100 grams in the arrow direction.



#### 11.2 Packaging Quantity

TYPE	PCS/REEL
160808	4000
201209	4000

#### 11.3 Reel Dimensions




TYPE	A	B	C	D
160808	178	60	12	1.5
201209	178	60	12	1.5

## BBGK00160808 Series Specification


### 11 Packaging:

#### 11.4 Tape Dimensions in mm



TYPE	A	B	T	W	P	F
160808	1.05	1.85	0.95	8	4	3.5
201209	1.50	2.30	0.97	8	4	3.5

### 12 Recommended Land Pattern:



Dimensions in mm


TYPE	A	B	C
160808	0.7 ~ 0.8	1.8 ~ 2.0	0.6 ~ 0.8

### 13 Note:

1. Please make sure that your product has been evaluated and confirmed against your specifications when our product is mounted to your product.
2. Do not knock nor drop.
3. All the items and parameters in this product specification have been prescribed on the premise that our product is used for the purpose, under the condition and in the environment agreed upon between you and us. You are requested not to use our product deviating from such agreement.
4. Please keep the distance between transformer/coil and other components (refer to the standard IEC 950)
5. The moisture sensitivity level (MSL) of products is classified as level 1.









# BBGK00160808 Series Specification

**14** Graph:



# BBGK00160808 Series Specification

**14** Graph:



# BBGK00160808 Series Specification

**14** Graph:

