



CIEL LIGHT CO.,LTD.

PRODUCT SPECIFICATION

Customer: _____

Customer's Model No.: _____

Customer's Drawing No.: _____

Model No.: CL-5074UWC1C-001(5000-7000K)

Drawing No.: _____


Features

- Low Power Consumption
- High Efficiency
- Round Type
- T1 (5mm) Diameter
- With Flange
- Solder Leads Without Stand-off
- Compliant With RoHS

Descriptions

- Chip Material: InGaN/GaN
- Emitting Color: White
- Lens Color: Water Clear

Outline Drawing



ATTENTION



OBSERVE PRECAUTIONS
FOR HANDLING
ELECTROSTATIC
SENSITIVE DEVICES

Tolerance is $\pm 0.25\text{mm}$ unless otherwise noted, Unit=mm
Pin bending $\leq \text{length} * 1\%$

Electrical Optical Characteristics (Ta=25°C)

Parameter	Symbol	White			Unit	Test Condition
		Min	Typ	Max		
Forward Voltage	V _F	---	3.20	3.60	V	IF=20mA
Luminous Intensity	I _V	1100	2180	---	med	IF=20mA
Chromaticity Coordinates	X	---	0.31	---	nm	IF=20mA
	Y	---	0.34	---	nm	IF=20mA
Spectral Line half-width	Δλ	----	30	----	nm	IF=20mA
Reverse Leakage Current	I _R	----	----	50	μA	VR=5V
Viewing Angle	2θ _{1/2}	---	60	----	Deg	IF=20mA

Absolute Maximum Parameters (Ta=25°C)

Parameter	Symbol	Condition	Rating	Unit
Power Dissipation	P _D	----	120	mW
Reverse Voltage	V _R	----	5	V
Forward Average Current	I _F	----	30	mA
Temperature Coefficient	I/C	---	0.4	mA/ °C
Pulse Current	IFP	Duty=1/10,1kHz	100	mA
Operating Temperature Range	Toopr	----	-25 ~ +85	°C
Storage Temperature Range	Tstg	----	-30 ~ +100	°C
Soldering Condition	Tsd	----	260°C/5sec	°C

NOTE:

Luminous Intensity Measurement allowance is ± 10%.

2θ_{1/2} is the off-axis angle at which the luminous intensity is half the axial luminous intensity.

The dominant wavelength is derived from the CIE chromaticity diagram and represents the single wavelength which defines the color of the device.



CIEL LIGHT CO.,LTD.

CL-5074UWC1C-001(5000-7000K)€


Forward Voltage BIN Table

Forward Voltage		Unit:V @20mA
BIN Code	Min	Max
2	2.8	2.9
3	2.9	3.0
4	3.0	3.1
5	3.1	3.2
6	3.2	3.3
7	3.3	3.4
8	3.4	3.5
9	3.5	3.6

Lighting Intensity BIN Table

Luminous Intensity		Unit:med @20mA
BIN Code	Min	Max
T	1100	1520
U	1520	1820
V	1820	2180
W	2180	2610
X	2610	3130
Y	3130	3750






Color Coordinate Comparison



Chromaticity Bin Table

BIN	X	Y	X	Y	X	Y	X	Y	X	Y
P3	0.2989	0.3213	0.3095	0.332	0.311	0.323	0.3011	0.3127	0.2989	0.3213
Q3	0.3095	0.332	0.3214	0.3434	0.3222	0.3331	0.311	0.323	0.3095	0.332
M3	0.3339	0.3545	0.3466	0.3646	0.345	0.3523	0.3338	0.3432	0.3339	0.3545
P4	0.3011	0.3127	0.311	0.323	0.3124	0.3142	0.303	0.305	0.3011	0.3127
Q4	0.311	0.323	0.3222	0.3331	0.3229	0.324	0.3124	0.3142	0.311	0.323
M4	0.3338	0.3432	0.345	0.3523	0.3443	0.3416	0.3332	0.3323	0.3338	0.3432

Typical Electro/Optical Characteristic Curves (Ta=25°C)



Reliability Test Conditions

Test Item	Test Condition	Result	Judgment Criteria
Consecutive operating life test	IF=20mA, T=25°C, t=168h	0/100	
High temperature storage life test	T=100°C, t=168h	0/100	
Low temperature storage life test	T=25°C, t=168h	0/100	Forward Voltage VF(V)= Upper Limit × 1.2 Reverse Leakage Current IR(µA)=Upper Limit × 2.0 Luminous Intensity IV (mcd)=Lower Limit × 0.7
High temperature humidity storage life test	T=85 ± 2°C, RH=85% ± 3, t=168h	0/100	
Temperature cycle test	-25°C~25°C~100°C 30min 5min 30min 10cycles	0/100	
Thermal shock test	100°C 0°C 5min 5min 20cycles	0/100	
Soldering heat test	T=260 ± 5°C, t=10s ± 1s	0/100	
Solderability test	T=235 ± 5°C, t=5s ± 0.5s	0/100	Steeped Part ≥ 95%
Fall test	h=100cm, 50times	0/100	
Terminal strength test	W=9.8N, t=30 ± 5s	0/100	Surface Appearance Photoelectric Properties Intact
Lead bending test	W=4.9N, 2times	0/100	